



TO REORDER CALL:
(281) 647-9700
or
1-800-295-BETA

Product Code:
2090-A

SURE TREAD

Non-Slip Grit Coating Clear

- Slip Resistant • For Indoor/Outdoor Use
- Starts Drying Immediately • Specially Designed Soft Grit
- Made with Durable Epoxy • Bonds with Virtually Any Surface

GREAT FOR THESE APPLICATIONS:

- PUBLIC RESTROOMS • STAIRS • LADDERS • LOADING DOCKS • HIGH TRAFFIC AREAS • RAMPS
- ENTRY WAYS • EMERGENCY EXITS • DIVING BOARDS • MARINE APPLICATIONS • POOL DECKS
- BATHTUBS • SHOWERS • ROOF HATCH LADDERS • AROUND EQUIPMENT AND MACHINERY
- WAREHOUSE PATHS • WHERE HAZARDOUS SLIPPERY CONDITIONS EXIST

DIRECTIONS:

Surface must be clean, dry and free of rust before painting. Protect surrounding areas from spray mist. For best results, use **SURE TREAD** when can is between 50°F and 90°F (10°C and 32°C). Shake **SURE TREAD** at least one minute after rattle is heard and occasionally during use. Spray **SURE TREAD** with steady even strokes at a distance of 6 to 10 inches (15 to 25cm). Several light coats give a better finish than one heavy coat. **SURE TREAD** is tack free in 60 minutes and fully cured in 24 hours. If clogging develops, turn sprayhead 1/4 turn or remove and clean sprayhead slot. DO NOT stick pin or other object into can opening. With can and sprayhead pointed away from you, reinsert sprayhead with a gentle twisting motion. To clear sprayhead for future use, turn **SURE TREAD** upside down and spray for 3 seconds. Completely empty cans may be recycled or disposed of with regular trash. Dispose of partially empty cans responsibly. DO NOT incinerate or compact.

BETA DATA

FLASH POINT:	-2°F (closed cup)	SOLUBILITY IN WATER:	Negligible
COLOR:	Clear	ODOR:	Solvent
PROPELLANT:	Propane / N-Butane	BIODEGRADABILITY:	No
STORAGE STABILITY:	1 yr. +	EVAPORATION RATE:	Unknown
SPECIFIC GRAVITY:	0.77 - 0.85	FORM:	Aerosol
COLD STABILITY:	Good	% VOLATILE BY VOLUME:	Aprx. 42.7

BETA TECHNOLOGY, INC.

CORPORATE HEADQUARTERS

P.O. Box 218686 • Houston, TX 77218-8686